



PRODUCT INFORMATION

TAROPRENE 2A60 E1G

Thermoplastic Elastomer Vulcanized. This TPE-V compound combines the typical performance of a vulcanized elastomer with the easy processing of a thermoplastic compound. Taroprene is totally recyclable and it can be produced in standard grades and in tailor-made grades.

ISO short Form ISO 18064: TPV-(EPDM+PP)
Pellets

Key Features

- Very light natural colour
- Designed for extrusion applications

Process

- INJECTION MOULDING

Application

- Household
- General purpose applications
- Furniture
- Consumer
- Building
- Automotive

| Property | Method | Unit | Value | Condition | State |
|------------------------------------|-------------|-------------------|-------|--------------|-------|
| PHYSICAL | | | | | |
| Density (+23°C) | ISO 1183 | g/cm ³ | 0,96 | | |
| Melt Flow Rate (MFR) | ISO 1133 | g/10 min | 6,0 | 190°C - 5 kg | |
| MECHANICAL | | | | | |
| Hardness SHORE A | ASTM D2240 | Shore A | 60 | 3 sec | |
| Tensile Break Strength | ASTM D412/C | MPa | 5,2 | | |
| Elongation at Break | ASTM D412/C | % | 610 | | |
| Tensile Modulus at 100% elongation | ASTM D412/C | MPa | 1,96 | | |
| Tensile Modulus at 300% Elongation | ASTM D412/C | MPa | 3,44 | | |
| Tear Strength | ASTM D624/C | N/mm | 28 | | |

The listed data are in the normal range of product properties, they should not be used to establish specification nor as the basis of design. Values are valid for natural coloured version only.

Unless specified to the contrary, the given values have been established on standardized test specimens at room temperature. These values are for natural colour only. The figures should be regarded as guide values only and not as binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions, pigments and any other additives.

All information, recommendation or technical advice provided by TARO PLAST S.p.A. are given in good faith but without warranty, to the best of its knowledge and based on current procedures in effect. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing methods and conditions of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely under your own responsibility.



PRODUCT INFORMATION

TAROPRENE 2A60 E1G

| | | | | |
|-----------------|-------------|---|----|-------------|
| Compression Set | ASTM D395/B | % | 35 | 70°C - 22h |
| Compression Set | ASTM D395/B | % | 42 | 100°C - 22h |

| INJECTION MOULDING | Value |
|--------------------------------------|--------------|
| Drying Temperature (Desiccant Dryer) | 80 - 90°C |
| Drying Time (Desiccant Dryer) | 3 h |
| Melt Temperature | 190 - 220°C |
| Rear Temperature | 180°C |
| Middle Temperature | 190°C |
| Front Temperature | 200°C |
| Die Temperature | 210°C |

Notes TAROPRENE is incompatible with POM and PVC. We recommend that all TAROPRENE products are always dried prior to use at the specified drying conditions.

The listed data are in the normal range of product properties, they should not be used to establish specification nor as the basis of design. Values are valid for natural coloured version only.

Unless specified to the contrary, the given values have been established on standardized test specimens at room temperature. These values are for natural colour only. The figures should be regarded as guide values only and not as binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions, pigments and any other additives.

All information, recommendation or technical advice provided by TARO PLAST S.p.A. are given in good faith but without warranty, to the best of its knowledge and based on current procedures in effect. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing methods and conditions of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely under your own responsibility.