



PRODUCT INFORMATION

**TAROPRENE 1D50 M1N**

Thermoplastic Elastomer Vulcanized. This TPE-V compound combines the typical performance of a vulcanized elastomer with the easy processing of a thermoplastic compound. Taroprene is totally recyclable and it can be produced in standard grades and in tailor-made grades. Available in natural (00), black (99) and colored grade (..).

**ISO short Form** ISO 1043: TPV-(EPDM+PP)  
Pellets

**Key Features**

- Designed for injection moulding applications

**Availability**

- All colours

**Process**

- INJECTION MOULDING

**Application**

- Household
- General purpose applications
- Furniture
- Consumer
- Automotive

Property	Method	Unit	Value	Condition	State
<b>PHYSICAL</b>					
Density (+23°C)	ISO 1183	g/cm <sup>3</sup>	0,96		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	4,0	190°C - 5 kg	
<b>MECHANICAL</b>					
Hardness SHORE D	ASTM D2240	Shore D	50	3 sec	
Tensile Break Strength	ASTM D412/C	MPa	19,8		
Elongation at Break	ASTM D412/C	%	520		
Tensile Modulus at 100% elongation	ASTM D412/C	MPa	13,1		
Tensile Modulus at 300% Elongation	ASTM D412/C	MPa	14,6		
Tear Strength	ASTM D624/C	N/mm	86		

**INJECTION MOULDING** **Value**

The listed data are in the normal range of product properties, they should not be used to establish specification nor as the basis of design. Values are valid for natural coloured version only.

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to both the health and the well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation systems and fresh air at the workplace in accordance with the product Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures and conditions should not be substantially exceeded.

All information, recommendation or technical advice provided by TARO PLAST S.p.A. are given in good faith but without warranty, to the best of its knowledge and based on current procedures in effect. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing methods and conditions of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely under your own responsibility.



PRODUCT INFORMATION

**TAROPRENE 1D50 M1N**

Drying Temperature (Desiccant Dryer)	80°C
Drying Time (Desiccant Dryer)	3 hours
Suggested Max Moisture	0,08%
Suggested Max Regrind	20%
Melt Temperature	215 - 230°C
Feed Temperature	170°C
Rear Temperature	195°C
Middle Temperature	200°C
Front Temperature	205°C
Nozzle Temperature	200 - 220°C
Mould Temperature	10 - 50°C
Injection Rate	Fast
Back Pressure	0,3 - 0,7 Mpa
Screw Revolving Speed	100 - 200 rpm
Clamp Tonnage	70 - 70 Mpa
Cushion	3 - 7 mm
Screw L/D Ratio	16 - 20
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,025 mm

**Notes** TAROPRENE is incompatible with POM and PVC. We recommend that all TAROPRENE products are always dried prior to use at the specified drying conditions.

*The listed data are in the normal range of product properties, they should not be used to establish specification nor as the basis of design. Values are valid for natural coloured version only.*

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to both the health and the well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation systems and fresh air at the workplace in accordance with the product Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures and conditions should not be substantially exceeded.

All information, recommendation or technical advice provided by TARO PLAST S.p.A. are given in good faith but without warranty, to the best of its knowledge and based on current procedures in effect. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing methods and conditions of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely under your own responsibility.